



SUPERLITE VE DATA SHEET - 003 Issue 4, Effective Date: 26/03/01

Chemical Name: stannic oxide, tin (IV) oxide, SnO₂

C.A.S. No: [18282-10-5]

CCCN No: 282590 30 0

EINECS No: 2421590

Description: Stannic oxide produced thermally from high grade tin metal

Physical state: Inert white powder, comprising aggregates of spherical primary particles. Non-flammable. Specific Gravity 6.95

CONTROL PROPERTIES

Chemical data: This material is produced from tin metal conforming to the BS EN 610 : 1996 specification (99.85% minimum purity)

Physical data: This material is manufactured and tested to conform to the following Sedigraph particle size distribution:

% Finer Than	Typical	Control Range
10 microns	99	97 to 100
5 microns	99	97 to 100
2 microns	98	96 to 100
1 microns	96	93 to 99
0.5 microns	79	64 to 94

Metallic tin: 0.02% maximum (I)

TYPICAL SIGNIFICANT PROPERTIES (II)

Surface Area (BET) m² g⁻¹ 7 to 11

Tap Density g l⁻¹ 600

Chemical data, impurities (as oxides):

As, Bi, Co, Cu, Fe, In, Ni, Pb, Sb Individual oxides 0.05% maximum

Ag, Cd, Mg, Mn, Zn Individual oxides 0.01% maximum

Total of all impurities listed 0.15% maximum

All information is given in good faith but without warranty.

This Data Sheet supersedes and replaces all previous issues.

(I) Keeling & Walker Limited test method KW10.

(II) Based on bulk samples assayed at intervals.

Keeling & Walker Test Methods are available for all the above determinations.

Keeling & Walker tin oxide is manufactured under a Quality Assurance System certified to comply with ISO 9000.